



**North American**  
**ADHESIVES®**

**NA 3700**

# Magna Lite™

**Lightweight, Thin-Set Mortar with Polymer**



## PRODUCT DESCRIPTION

NA 3700 Magna Lite is a premium-grade, lightweight, thin-set mortar fortified with polymer for enhanced bonding to ceramic, porcelain, quarry, pavers and most marble, granite and natural-stone tiles. This formula is also good for large-and-heavy-tile installations on floors and non-sag applications on walls. NA 3700 Magna Lite provides twice the coverage of a standard mortar per pound/kg. It has a smooth and creamy consistency, and is mold- and mildew-resistant.

## FEATURES AND BENEFITS

- Polymer-enriched for high performance and deformability
- Non-sag formula for large and heavy tile and stone in wall applications
- Nonslump for large and heavy tile and stone in floor applications
- A 25-lb. (11.3-kg) bag provides the same coverage as a 50-lb. (22.7-kg) bag of a standard polymer-modified mortar.
- Ideal for installations with light-colored stones and translucent marble
- Smooth and creamy consistency
- For thicker bond coats from 3/32" to 1/2" (2.5 to 12 mm)

## INDUSTRY STANDARDS AND APPROVALS

- ISO 13007: Classification C2TES1P1
- ANSI: Exceeds ANSI A118.4TE, ANSI A118.11 and ANSI A118.15TE requirements
- SCS Green Squared Certified per ANSI A138.1

### Green Certifications

Living Building Challenge (LBC) Red List Free: This product has been verified per the most current Red List on the LBC's Website.

## USES

- For most interior/exterior residential and commercial installations on floors and walls
- For installation of ceramic and porcelain tile, quarry tile, pavers, Saltillo tile, and most types of marble, granite and natural-stone tiles

## SUBSTRATE REQUIREMENTS

- All substrates should be structurally sound, stable, dry, clean and free of any substance or condition that may reduce or prevent proper adhesion.
- Substrates to receive thin porcelain tiles must be perfectly flat. When installing thin-body porcelain tile, consult Technical Services. Thin-body porcelain tile refers to tiles that are 1/8" to 1/4" (3 to 6 mm) thick for walls and 3/16" to 1/4" (4.5 to 6 mm) thick for floors.

### Tile Council of North America (TCNA) Maximum Allowable Deflection for Floor Systems and Substrates

Floor systems, whether wood framed or concrete, over which the tile will be installed using the appropriate TCNA method, according to the Floor Tiling Installation Guide, shall be in conformance with the International Residential Code (IRC) for residential applications, the International Building Code (IBC) for commercial applications, or applicable building codes. ... The owner should communicate in writing to the project design professional and general contractor the intended uses of the tile installation, including in-service loads or information to allow a project design professional to calculate such. ... The tile contractor shall not be responsible for problems resulting from any structural subfloor installation not compliant with applicable building codes, unless structural subfloor was designed and installed by tile contractor, nor for problems from overloading.

Please reference the most current version of the TCNA handbook for more complete substrate requirements.

Consult Technical Services for installation recommendations regarding substrates and conditions not listed.

## SUITABLE SUBSTRATES

- Concrete (cured for at least 28 days)
- Masonry cement block, brick, cement mortar beds, render coats and leveling coats



**NA 3700**

# Magna Lite™

- Cement backer units (CBUs) – see manufacturer’s installation guidelines
- Gypsum wallboard and plaster – interior walls in dry areas only (priming may be required)
- APA Group 1 and CANPLY 0121 exterior-grade plywood (interior, residential and light commercial floors and countertops in dry conditions only)
- Properly prepared vinyl composition tile (VCT), vinyl and cutback residue (interior only)
- Properly prepared existing ceramic and porcelain tile, quarry tile and pavers (interior only)
- North American Adhesives (NAA) waterproofing, crack-isolation, sound-reduction and uncoupling membranes (limited to thin-set installations only when using weak stone)

## LIMITATIONS

- Install only at temperatures between 40°F and 95°F (4°C and 35°C).
- Do not use for moisture-sensitive stone (green marble; some limestone and granites), agglomerate tiles or resin-backed tiles. Instead, use suitable epoxy or urethane adhesives. See the respective Technical Data Sheets for more information.
- Do not use over dimensionally unstable substrates such as hardwood flooring, oriented strand board (OSB), substrates containing asbestos, or metal.
- To use directly over gypsum-based patching or leveling substrates, apply a suitable primer/sealer before use.
- Installations of tile over nonporous surfaces, such as waterproofing membranes and existing tile, may require extended setting/curing times.
- Do not use for installations subject to water immersion, such as pools and spas.
- Not recommended for areas subject to severe freeze/thaw conditions. For the best performance, use a NAA mortar system with a liquid latex additive.

## MIXING

Before product use, take appropriate safety precautions. Consult the Safety Data Sheet for safe-handling instructions.

1. Pour clean, potable water into a clean mixing container.
  - For thin-set applications: Use about 5.5 U.S. qts. (5.20 L) of water. Refer to Step 2 for the final water addition.

- For large-and-heavy-tile and non-sag wall applications: Use about 5 U.S. qts. (4.73 L) of water. Refer to Step 2 for the final water addition.
2. Gradually add 25 lbs. (11.3 kg) of powder while slowly mixing for at least 1 minute. Adjust the consistency with water, adding up to 1 additional U.S. qt. (946 mL) as needed, without overwatering. Mix again for 2 minutes.
  3. Use a low-speed mixing drill (at about 300 rpm) with an angled cross-blade mixer or auger mixer. Mix thoroughly until the mixture becomes a smooth, homogenous, lump-free paste. Avoid prolonged mixing.
  4. Let the mixture stand (“slake”) for 5 to 10 minutes.
  5. Remix.
  6. If mixture becomes heavy or stiff, remix without adding more liquid.

## APPLICATION

1. Choose a notched trowel (see the “Approximate Coverage” chart) with sufficient depth to achieve greater than 80% mortar contact to both the tile and substrate for all interior applications, and greater than 95% for exterior installations, commercial floor and wet applications. It may be necessary to back-butter the tile to meet these requirements. (Refer to ANSI A108.5 specifications and TCNA handbook guidelines.)
2. With pressure, apply a coat by using the trowel’s flat side to key the mortar into the substrate.
3. Apply additional mortar, combing it in a single direction parallel to the tile’s shortest dimension, with the trowel’s notched side. If thin tile is being installed, it should be placed so that the trowel ridges on its back are oriented in the same parallel direction as the trowel ridges on the substrate.
4. Spread only as much mortar as can be tiled before the product skins over. Open time can vary with jobsite conditions.
5. Place the tiles firmly into the wet mortar. Push the tiles back and forth in a direction perpendicular to trowel lines, to collapse the mortar ridges and to help achieve maximum coverage. Ensure proper contact between the mortar, tile and substrate by periodically lifting a few tiles to check for acceptable coverage.
6. Remove excess mortar from the joint areas so that at least 2/3 of the tile depth is available for grouting (see ANSI A108.10 guidelines).

## EXPANSION AND CONTROL JOINTS

- Provide for expansion and control joints as specified per TCNA Method EJ171 or TTMAC Specification Guide 09 30 00, Detail 301MJ. Do not cover expansion joints with mortar.

**NA 3700**

# Magna Lite™

## CLEANUP

- Clean tools and tile while the mortar is fresh, using only water.

## PROTECTION

- Do not disturb the flooring installation, allow light traffic or grout any tiles for at least 24 to 48 hours.
- Protect the flooring installation from general traffic for at least 72 hours and from heavy traffic for at least 7 days.
- Protect any exterior installation from rain for 72 hours and from freezing for 21 days.

Note: When working in cold temperatures, protect tilework for an extended time for this dry-set mortar to cure before grouting and/or allowing traffic.

## Product Characteristics

at 73°F (23°C) and 50% relative humidity

Color	Neutral
Packaging	Bag: 25 lbs. (11.3 kg)
VOCs (Rule #1168 of California's SCAQMD)	0 g per L
Shelf life	1 year when stored in original, unopened packaging
Open time*	30 minutes
Pot life*	> 2 hours
Time before grouting (walls)*	8 to 16 hours
Time before grouting (floors)*	24 to 48 hours

\* Actual open time, pot life and time before grouting will vary based on jobsite conditions.

## ISO 13007 Classification

Classification Code	Classification Requirement	Test Characteristic
C2 (cementitious, improved adhesive)	≥ 145 psi (1 MPa) after standard aging, heat aging, water immersion and freeze/thaw cycles	Using porcelain tile
T (slip resistance)	≤ 0.019" (0.5 mm)	Using porcelain tile
E (extended open time)	≥ 72.5 psi (0.5 MPa) after 30 minutes	Using glazed ceramic wall tile
S1 (normal deformation of mortar)	≥ 0.1" (2.5 mm)	—
P1 (normal adhesion to plywood)	≥ 72.5 psi (0.5 MPa)	Using porcelain tile

**NA 3700**

# Magna Lite™

ANSI Specification*		
Test Method	Specification Standard	Test Results
ANSI A118.11 – shear strength, quarry tile to plywood	> 150 psi (1.03 MPa) at 28 days	150 to 250 psi (1.03 to 1.72 MPa)
ANSI A118.15E – extended open time	≥ 72.5 psi (0.5 MPa) at 30 minutes	Pass
ANSI A118.15 – shear strength, impervious ceramic (porcelain) mosaics	> 400 psi (2.76 MPa) at 28 days	Pass
ANSI A118.15 – shear strength, glazed wall tile	> 450 psi (3.10 MPa) at 7 days	450 to 650 psi (3.10 to 4.48 MPa)
ANSI A118.15 – shear strength, quarry tile to quarry tile	> 150 psi (1.03 MPa) at 28 days	400 to 600 psi (2.76 to 4.14 MPa)
ANSI A118.15T – sag on vertical surfaces	≤ 0.02" (0.5 mm) at 20 minutes	Pass

\* Anything that meets A118.15 by definition exceeds A118.4.

Approximate Coverage** per 25 lbs. (11.3 kg)	
<b>For thin-set applications</b>	
1/4" x 1/4" x 1/4" (6 x 6 x 6 mm), square-notch	75 to 90 sq. ft. (6.97 to 8.36 m <sup>2</sup> )
1/4" x 3/8" x 1/4" (6 x 10 x 6 mm), square-notch	55 to 65 sq. ft. (5.11 to 6.04 m <sup>2</sup> )
<b>For large-and-heavy-tile and non-sag wall applications</b>	
1/4" x 1/4" x 1/4" (6 x 6 x 6 mm), square-notch	75 to 90 sq. ft. (6.97 to 8.36 m <sup>2</sup> )
1/4" x 3/8" x 1/4" (6 x 10 x 6 mm), square-notch	55 to 65 sq. ft. (5.11 to 6.04 m <sup>2</sup> )
1/2" x 1/2" x 1/2" (12 x 12 x 12 mm), square-notch	38 to 45 sq. ft. (3.53 to 4.18 m <sup>2</sup> )
3/4" x 9/16" x 3/8" (19 x 14 x 10 mm), U-notch	25 to 30 sq. ft. (2.32 to 2.79 m <sup>2</sup> )

\*\* Trowel dimensions are width/depth/space. Coverage shown is for estimating purposes only. Actual coverage depends on substrate profile and porosity, equipment used, thickness applied, temperature and humidity.

## LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in effect at the time of the NAA product installation. For the most up-to-date TDS and warranty information, visit our Website at [www.na-adhesives.com](http://www.na-adhesives.com). **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED NAA WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**