



North American
ADHESIVES®

NA 500

Floor Patch

Rapid-Setting Patching Compound with Polymer



PRODUCT DESCRIPTION

NA 500 Floor Patch is a fast-setting, latex-fortified, sanded cement-based patching compound with high compressive strength. When *NA 500 Floor Patch* is mixed with water, floor coverings can be installed in just 1 hour after application. When mixed with the latex liquid *NA 501 Floor Patch Additive*, *NA 500 Floor Patch* can be used as an embossing leveler or to encapsulate cutback adhesive residue.

USES

- For skimcoating unfinished, rough-textured concrete and approved wood underlayments
- For filling minor voids, holes and cracks in concrete and approved wood underlayments
- Interior residential (apartments, condominiums and homes)
- Interior commercial (office buildings, hotel rooms/hallways, restaurants and cafeterias)
- Interior heavy commercial (hotel lobbies, convention centers, airports, shopping malls, grocery stores and department stores)
- Interior institutional (hospitals, schools, universities, libraries and government buildings)
- When mixed with *NA 501 Floor Patch Additive*, use as an embossing leveler or as a patch to fill voids over properly prepared existing cement terrazzo, ceramic tile, vinyl composition tile (VCT), or non-cushioned, fully adhered residential sheet vinyl flooring, cutback and carpet adhesive residues.

SUBSTRATE REQUIREMENTS

- All substrates must be structurally sound, dry, solid and stable.

- The substrate should be clean and free of dust, dirt, oil, grease, paint, curing agents, concrete sealers, loosely bonded toppings, loose particles, epoxy adhesives, urethane adhesives, and any other substance or condition that may prevent or reduce adhesion.
- Concrete must be free of any negative hydrostatic pressure and/or excessive moisture.
- See the "Surface Preparation for Tile and Stone Installations" reference guide in the Document Library section of North American Adhesives' Website at www.na-adhesives.com.

Tile Council of North America (TCNA) Statement on Deflection Criteria

Floor systems, including the framing system and subfloor panels, over which tile will be installed should be in conformance with the IRC [International Residential Code] for residential applications, the IBC [International Building Code] for commercial applications, or applicable building codes.

Note: The owner should communicate in writing to the project design professional and general contractor the "intended use" of the tile installation, in order to enable the project design professional and general contractor to make necessary allowances for the expected live load, concentrated loads, impact loads, and dead loads including the weight of the tile and setting bed. The tile installer shall not be responsible for any floor framing or subfloor installation not compliant with applicable building codes, unless the tile installer or tile contractor designs and installs the floor framing or subfloor.

Consult Technical Services for installation recommendations regarding substrates and conditions not listed.



NA 500

Floor Patch

SUITABLE SUBSTRATES

When mixed with water or diluted NA 501 Floor Patch Additive

- Concrete
- APA or CANPLY Group 1 exterior-glue plywood
- Other approved wood underlayments (per flooring manufacturer's recommendations)

When mixed with NA 501 Floor Patch Additive (full strength)

- Properly prepared cutback and carpet adhesive residue
- Existing, properly prepared cement terrazzo
- Existing, properly prepared and fully bonded ceramic tile
- A single layer of properly prepared, fully bonded VCT
- A single layer of properly prepared, fully bonded, felt-backed sheet vinyl

LIMITATIONS

- Use only when the substrate and ambient temperatures are between 50°F and 100°F (10°C and 38°C).
- Do not install over substrates containing asbestos.
- Do not use as a final wear surface.
- Do not use for exterior applications.
- Do not apply over self-stick tile, presswood, particleboard, flakeboard or similar types of dimensionally unstable substrates.
- Do not install when the moisture vapor emission rate (MVER) exceeds 8 lbs. per 1,000 sq. ft. (3.63 kg per 92.9 m²) per 24 hours, when using the anhydrous calcium chloride test (ASTM F1869). Do not exceed the flooring manufacturer's recommendations for MVER. When the MVER is above 5 lbs. per 1,000 sq. ft. (2.27 kg per 92.9 m²) per 24 hours, NA 501 Floor Patch Additive is recommended for optimum performance.
- Do not install when the relative humidity (RH) exceeds 85%, when using the in-situ probe method (ASTM F2170). Do not exceed the flooring manufacturer's recommendations for RH.
- Do not use to fill existing expansion control joints.
- When leveling large areas, use as a thin application only.

MIXING

Consult the Safety Data Sheet for safe-handling instructions. See the Technical Data Sheet for NA 501 Floor Patch Additive for detailed instructions on diluting NA 501 Floor Patch Additive with water.

Depending on the application, NA 500 Floor Patch can be mixed with water or NA 501 Floor Patch Additive. Due to the short pot life of NA 500 Floor Patch, it is not recommended to mix an entire bag of NA 500 Floor Patch at one time.

Liquid options per 10 lbs. (4.54 kg) of NA 500 Floor Patch powder

Option A, water = Add 45 to 50 U.S. oz. (1.33 to 1.48 L).

Option B, diluted NA 501 Floor Patch Additive = Add 45 to 57 U.S. oz. (1.33 to 1.69 L).

Option C, full-strength NA 501 Floor Patch Additive = Add 57 to 62 U.S. oz. (1.69 to 1.83 L).

Single-coat application – For skimcoating and filling minor voids in concrete and wood substrates, mix NA 500 Floor Patch with water (Option A). For a smoother and creamier consistency, or for bonding over smooth concrete, use diluted NA 501 Floor Patch Additive (Option B).

Two-coat application – For using NA 500 Floor Patch as an embossing leveler or to patch over properly prepared cement terrazzo, ceramic tile, existing VCT or existing non-cushioned, fully adhered residential sheet vinyl flooring, mix NA 500 Floor Patch with full-strength NA 501 Floor Patch Additive (Option C) for the first coat. Then mix NA 500 Floor Patch with diluted NA 501 Floor Patch Additive (Option B) for a second coat.

1. Some settling may occur during transportation. Dry-blend NA 500 Floor Patch powder before mixing.
2. Into a clean mixing container, pour the required amount of liquid and then powder.

Note: Water temperature should not exceed 73°F (23°C). Higher water temperature will shorten pot life.
3. Do not overwater.
4. Use a low-speed mixer (at about 300 rpm) to mix for no more than 2 minutes. Mix thoroughly to a smooth, lump-free consistency.
5. Do not mix more material than can be applied within 8 to 10 minutes.
6. Avoid air entrapment and prolonged mixing, which will shorten pot life.

NA 500

Floor Patch

APPLICATION

Single-coat application method

1. Select a flat-edged steel trowel.
2. Immediately apply mixed *NA 500 Floor Patch* (Option A or Option B) to the substrate, according to the desired thickness – up to 1/2" (12 mm) for Option A, or from 1/32" to 1/4" (1 to 6 mm) for Option B. Blend the application into the surrounding area and finish to the required smoothness.
3. Allow the application to dry for at least 60 minutes, finishing it with the final floor covering chosen.

Two-coat application method

1. Select a flat-edged steel trowel.
2. First coat: Immediately apply a mixture of *NA 500 Floor Patch* and full-strength *NA 501 Floor Patch Additive* (Option C) to the substrate according to the desired thickness – from 1/16" to 1/8" (1.5 to 3 mm). Blend the application into the surrounding area, finishing it to the required smoothness. Allow the application to dry completely.
3. Second coat: Immediately apply a mixture of *NA 500 Floor Patch* and diluted *NA 501 Floor Patch Additive* (Option B) to the substrate according to the desired thickness – from 1/32" to 1/4" (1 to 6 mm). Ensure that all areas with a first coat are completely covered by a second coat. Allow the application to dry for at least 60 minutes; thicker applications may require longer drying times before the application of flooring adhesives.

CLEANUP

- Clean tools and equipment with water while the product is still wet/fresh. Use mechanical means to remove any dried product.

PROTECTION

- Provide for dry, heated storage on site and deliver materials at least 24 hours before work begins.
- Protect from traffic, dirt or dust from other trades until the final installation of the floor covering.
- Because temperature and humidity (during and after tile installation) affect the final curing time, allow for extended periods of cure and protection when temperatures drop below 60°F (16°C) and/or when the relative humidity is higher than 70%.

Product Characteristics

at 73°F (23°C) and 50% RH

Packaging	Bag: 25 lbs. (11.3 kg)
Pot life	8 to 10 minutes
Drying time required before floor-covering installation*	60 to 90 minutes, or once the product is completely dry
Compressive strength, at 28 days (ASTM C109)	> 3,500 psi (24.1 MPa)
Cleanability	With water while still fresh
Shelf life	1 year when stored in original, unopened packaging in a heated area

* Drying time may vary based on temperature, humidity, substrate porosity, thickness of application and jobsite conditions.

Approximate Coverage** per 25 lbs. (11.3 kg)

Thickness Applied	Coverage
1/32" (1 mm)	100 to 140 sq. ft. (9.29 to 13.0 m ²)
1/8" (3 mm)	25 to 35 sq. ft. (2.32 to 3.25 m ²)

** Coverage shown is for estimating purposes only. Actual jobsite coverage may vary according to application method, substrate, substrate conditions and actual thickness applied.



North American
ADHESIVES®

NA 500

Floor Patch



North American
ADHESIVES®

MAPEI® Corporation
1144 East Newport Center Drive
Deerfield Beach, FL 33442

U.S. and Puerto Rico

Customer Service: 1-800-747-2722
Technical Services: 1-800-637-7753

© 2022 MAPEI Corporation
All Rights Reserved.
Printed in the USA.

Edition Date: June 10, 2022

Canada

1-844-410-1212

Refer to the Safety Data Sheet for specific data related to health and safety as well as product handling.
For the most current product data and warranty information, visit www.na-adhesives.com.

For information on sustainability and transparency, as well as product certification programs,
contact Technical Services at 1-800-637-7753.

MKT: 22-2061

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in effect at the time of the NAA product installation. For the most up-to-date TDS and warranty information, visit our Website at www.na-adhesives.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED NAA WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**